

Petrothene

GA501

Linear Low Density Polyethylene
Film Extrusion Grade

Melt Index 1.0 Density 0.918



Applications

The *Petrothene* GA501 series of resins is pelletized linear low density polyethylene for film extrusion applications that require excellent drawdown and toughness. These resins have excellent puncture resistance, elongation and heat seal strength. Applications include heavy duty shipping sacks, prime liners, commercial and industrial packaging, as well as food and consumer packaging.

Regulatory Status

The GA501 series resins meet the requirements of the Food and Drug Administration, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in " ...articles or components or articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information GA501 is available without additives or fully formulated with slip and antiblock additives.

Processing Techniques

Recommended conditions are 400°-450°F melt temperature and a 1.5-3.0:1 blow-up ratio. Using proper techniques, these products can readily be drawn below 0.90 mils at optimum production rates. Specific recommendations for type of resin and extrusion conditions can be made only when the end use, required properties and processing equipment are known. For further suggestions, please contact your Equistar sales representative.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index (190/2.16)	1.0	g/10 min	D 1238
Density	0.918	g/cc	D 1505
Vicat Softening Point	107	°C	D 1525
Film			
Gauge	1.0	mil	
Blow-up Ratio	2.5:1		
Haze	20	%	D 1003
Gloss, 45°	40		D 523
Dart Drop Impact Strength, F ₅₀	100	g	D 1709/A
Tensile Strength @ Break, MD (TD)	6,600 (4,700)	psi	D 882
Elongation @ Break, MD (TD)	580 (725)	%	D 882
1% Secant Modulus, MD (TD)	27,000 (28,000)	psi	D 638
Elmendorf Tear, MD (TD)	125 (330)	g	D 1922

Product	GA501020	GA501021	GA501022	GA501023
Slip	0	0	1350	900
Antiblock	0	7000	7000	5500

Equistar Chemicals, LP, is a member of the LyondellBasell group companies.

Petrothene is a trademark owned or used by LyondellBasell group companies. Trademark *Petrothene* is registered in the U.S. Patent and Trademark Office.

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

Equistar Chemicals, LP
1221 McKinney, Suite 700
P. O. Box 2583
Houston, Texas 77252-2583
(800) 615-8999
www.lyondellbasell.com

5677/0610