



Petrothene®

NA951000

Low Density Polyethylene
Film Extrusion Grade

Melt Index 2.2 Density 0.920

Applications

PETROTHENE NA951000 is specially designed for industrial and consumer packaging and liner and bag applications. NA951000 has an excellent balance of processability, toughness and drawdown and does not contain slip or antiblock..

Regulatory Status

NA951000 meets the requirements of the Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "...articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for further information regarding the suitability of specific products for specific applications.

Processing Techniques

Specific recommendations for processing NA951000 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.

Typical Properties

Property	Nominal Value	Units	ASTM Test Method
Melt Index	2.2	g/10 min	D 1238
Base Resin Density	0.920	g/cc	D 1505
Vicat Softening Point	90	°C	D 1525
Film¹			
Dart Drop Impact Strength, F ₅₀	100	g	D 1709
Tensile Strength @ Break MD (TD)	3,600 (2,500)	psi	D 882
Elongation, MD (TD)	250 (520)	%	D 882
1% Secant Modulus, MD (TD)	28,500 (33,000)	psi	E 111
Elmendorf Tear Strength, MD (TD)	320 (100)	g	D 1922
Molding*			
Tensile Strength	1,970	psi	D 638
Elongation @ Break	600	%	D 638

These are typical values and not to be construed as specific product limits.

* Data derived from type IV specimen, 75 mil plaque @ 20" min.

¹ Data obtained from film produced in a 3½" (89 mm) blown film line, commercially available 8" (203 mm) die, 350°F (177°C) melt extrusion temperature, 2:1 BUR, 1.25 mil (32 micron) gauge, 0.025 die gap at 150 lb/hr.

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.

® Petrothene is a registered trademark of Equistar Chemicals, LP.



Lyondell Chemical Company
1221 McKinney, Suite 700
P.O. Box 2583
Houston, Texas 77252-2583
800.615.8999
<http://www.Lyondell.com>