

**Preliminary
Data Sheet**

Starflex

GM1810BB

Metallocene Linear Low Density Polyethylene
Film Extrusion Grade

Melt Index 1.0 Base Resin Density 0.918

Applications

Starflex GM1810BB is a pelletized mLLDPE resin for use in applications that require maximum strength and toughness. GM1810BB contains a processing aid and antiblock, but does not contain slip.

**Regulatory
Status**

GM1810BB meets the requirements of the Food and Drug Administration 21 CFR 177.1520. This regulation allows for, among other things, the use of this olefin polymer in " ...articles or components or articles intended for use in contact with food." Certain limitations or conditions of use may apply. Contact your Equistar sales representative for more information.

**Processing
Techniques**

Recommended processing conditions for GM1810BE are a 400° - 450°F melt temperature and a 1.5 to 3.0 blow-up ratio. Using proper techniques, these products can readily be drawn below 0.9 mils at optimum production rates. Specific recommendations for type of mLLDPE resin and extrusion conditions can only be made when the end use, required properties and extrusion equipment are provided; however, Equistar recommends that users conduct performance testing on finished articles in order to make an independent determination that GM1810BB is suitable and safe for all intended uses and applications. For further information, please contact your Equistar sales representative.

**Typical
Properties**

Resin	Nominal Value	Units	ASTM Test Method
Melt Index (190/2.16)	1.0	g/10 min	D 1238
Base Resin Density	0.918	g/cc	D 1505
Product Density	0.922	g/cc	D 1505
Film			
Gauge	0.75	mil	
Blow-up Ratio	2.5:1		
Haze	16	%	D 1003
Gloss, 45°	45	units	D 2457
Dart Drop Impact Strength, F ₅₀	600	g	D 1709/A
Tensile Strength @ Break MD (TD)	9,800 (8,600)	psi	D 882
Elongation @ Break, MD (TD)	470 (570)	%	D 882
1% Secant Modulus, MD (TD)	27,000 (28,000)	psi	D 882
Elmendorf Tear, MD (TD)	150 (260)	g	D 1922

The values listed for physical properties are nominal values only and are subject to normal variations consistent with the test methods and/or variations found acceptable to the industry.

Additives

Slip	0	ppm
Antiblock	4,500	ppm
Processing Aid	Yes	

Equistar Chemicals, LP, is a member of the LyondellBasell group companies.

Starflex is a trademark owned or used by LyondellBasell group companies. Trademark *Starflex* is registered in the U.S. Patent and Trademark Office.

The information on this document is, to our knowledge, true and accurate. However, since the particular uses and the actual conditions of use of our products are beyond our control, establishing satisfactory performance of our products for the intended application is the customer's sole responsibility. All uses of Equistar products and any written or oral information, suggestions or technical advice from Equistar are without warranty, express or implied, and are not an inducement to use any process or product in conflict with any patent.

Equistar materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues. Equistar makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

More detailed safety and disposal information on our products is contained in the Material Safety Data Sheet (MSDS). All users of our products are urged to retain and use the MSDS. A MSDS is automatically distributed upon purchase/order execution. You may request an advance or replacement copy by calling our MSDS Hotline at 800.700.0946.